

What is claimed is:

1. A phenolic molding composition comprising:
a resol-based phenolic resin; and
40 to 100 parts by weight of inorganic fiber;
5 30 to 90 parts by weight of natural silica powder with
an average particle diameter of from 20 to 150 μm ; and
1 to 15 parts by weight of a rubber component, each per
100 parts by weight of the resol-based phenolic resin.
- 10 2. The phenolic molding composition according to claim 1,
wherein the inorganic fiber includes 50% or more by weight
of glass fiber.
3. The phenolic molding composition according to claim 1,
15 wherein the natural silica powder is shaped like pulverized
powder.
4. The phenolic molding composition according to claim 2,
wherein the natural silica powder is shaped like pulverized
20 powder.
5. The resin pulley molded of a phenolic molding composition
defined in any one of claims 1 to 4.

25